



SKANDIA

5000 N. Highway 251 ■ Davis Junction, IL 61020
815.393.4600 ■ 800.945.7135
www.SkandiaInc.com

Client: Lamin-Art
1670 Basswood Road
Schaumburg IL 60173 USA

WO #: 196003-09
Date: 02/26/09
Test Plan #:
PO #: Verbal

Aircraft:
Stock

S/N: N/A
Tail #: N/A
Test ID #: 12NW-109813

VERTICAL FLAMMABILITY TEST RESULTS

14 CFR Part 25.853 (a) Amdt 25-116 Appendix F Part I (a)(1)(ii)

Conditioning Room: Time In: 02/25/09 10:45 AM Time Out: 02/26/09 11:31 AM

Specimen: Laminart, Inc.: Laminate, SG FR, Light Brown, D/L 5266513-5

| Flame Application (seconds) | Flame Time (seconds) | Burn Length (inches) | Drippings (seconds) |
|-----------------------------|----------------------|----------------------|---------------------|
| 12 | 0.0 | 0.4 | 0.0 |
| 12 | 1.2 | 0.5 | 0.0 |
| 12 | 7.1 | 0.5 | 0.0 |
| Average: | 2.8 | 0.5 | 0.0 |

Comments:

Vertical (12 sec.) Burn Test: Average Self-Extinguish time may not exceed 15 sec. Average Burn Length may not exceed 8". Average Dripping may not exceed 5 sec. after falling.

Passed: Failed :

Signed: Donna J. Parrish
Donna J. Parrish